

Remarks


The paragraph beginning on page 1, line 3 is amended to change the wording of the priority claim from "priority to" to "benefit of."

Claims 16, 61, and 79 as well as the paragraph beginning on page 29, line 3, page 43, line 11, and page 48, line 1 are each amended to change "2-hydroxy-2-methyl-1-phenyl-1-propane" to 2-hydroxy-2-methyl- 1-phenyl-propan-1-one" which is the correct name for DAROCUR 1173. The manufacture product description is attached for the convenience of the Examiner. No new matter is added by these amendments.

Claim 49 is amended to change the dependency from claim 48 to claim 82. This amendment was previously submitted but the claim was improperly designated. Accordingly, the amendment is being resubmitted.

Respectfully submitted,

Roy C. Krohn

By 
James W. Proscia
Reg. No. 47,010
Attorney/Agent for Applicant

Date: 2/4/05

BROOKS KUSHMAN P.C.
1000 Town Center, 22nd Floor
Southfield, MI 48075-1238
Phone: 248-358-4400
Fax: 248-358-3351




Ciba[®] DAROCUR[®] 1173 Photoinitiator

General

DAROCUR 1173 is a versatile highly efficient liquid photoinitiator which is used to initiate the photopolymerisation of chemically unsaturated prepolymers - e.g. acrylates - in combination with mono- or multifunctional monomers.

Chemical Structure




2-Hydroxy-2-methyl-1-phenyl-propan-1-one

Molecular weight: 164.2

CAS No. 7473-98-5

Absorption Spectrum (% in Acetonitrile)



Physical Properties

Appearance: colorless to slightly yellow liquid

Odor: slight

Miscibility: in most common organic solvents as well as most acrylate based monomers exceeds 50g/100g; practically insoluble in water.

Melting point: 4°C

Boiling point (at 0.13 mbar ~ 0.1 Torr): 80 - 81°C

Flashpoint: > 100°C

Density: 1.08 g/cm³

Viscosity (at 20°C): 25 mPa's

Application

DAROCUR 1173 may be used after adequate testing for applications such as UV curable clear coatings based on acrylates for paper, metal

Ciba® DAROCUR® 1173

Photoinitiator



Ciba

and plastic materials.

As a liquid UV curing agent with excellent compatibility, DAROCUR 1173 is especially easy to incorporate. It is therefore highly suitable for blends with other photoinitiators.

DAROCUR 1173 is especially recommended when UV coatings are required to exhibit only minimal yellowing even after prolonged exposure to sunlight. Yellowing of urethane acrylates may be further reduced by addition of Ciba Specialty Chemicals' hindered amine light stabilizer TINUVIN® 292.

The amount of DAROCUR 1173 required for optimum performance should be determined in trials covering a concentration range.

Recommended concentrations :

film thickness :	5 - 20 µm	2.0 - 4.0 % DAROCUR 1173
film thickness :	20 - 200 µm	1.0 - 3.0 % DAROCUR 1173

Safety and Handling

DAROCUR 1173 should be handled in accordance with good industrial practice. Detailed information is provided in the Safety Data Sheet.

Trademark

DAROCUR is a registered trademark.

Important Notice

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.